



OKS 416

Low-Temperature and High-Speed Grease



Description

OKS 416 is a low temperature and high speed grease.

Applications

- For lubrication points of all kinds as slide ways, spindles, geared parts of the electronic, precision engineering and optical equipment, temporarily or permanently exposed to extreme low temperatures like in arctic climates or cold storages
- Roller bearing lubrication of high-speed bearings, e.g. spindle bearings, miniature or precision bearings in machine-tools or textile machines, measuring equipment, electric motors of control technology and precision mechanics

Branches

- Iron and steel industry
- Glass and foundry industry
- Logistics
- Shipbuilding and marine technology
- Rail vehicle technology
- Chemical industry
- Paper and packaging industry
- Rubber and plastic processing
- Municipal services
- Plant and machine (tool) engineering

Application tips

For best results clean the lubrication point with OKS 2610/OKS 2611 Universal Cleaner. Remove the corrosion protection media before initial filling. Fill the bearings in a way that all the functional surfaces are lubricated sufficiently. Slow moving bearings (DN-value < 50,000) should be filled completely. Fast running bearings (DN-value >400,000) should be filled to 1/4, normal moving bearings to 1/3 of the free inner housing space. Observe the instructions of the bearing or machine manufacturer. Relubrication with a grease gun on to the grease nipples or with an automatic lubrication system. Relubrication intervals and amount to be defined acc. to the service conditions. If the removal of the old grease is not possible the amount of grease has to be limited to avoid excess lubrication of the bearing. For longer relubrication intervals, a complete exchange of the old grease is recommended. Mix with appropriate lubricants only.

Advantages and benefits

- Dynamic light noise proofed long-term lubrication grease
- Best use at arctic conditions and very high speed
- High efficiency through optimal formulation
- Multifunctional application beside the regular range of performance for greases
- Efficient through economical application
- No nameable change of consistency at low temperatures or high speeds and accordingly temperatures
- Oxidation stable and resistant against cold and hot water

OKS 416

Low-Temperature and High-Speed Grease

Packaging

- 400 ml Cartridge
- 1 kg Can
- 5 kg Hobbock

Technical data

	Standard	Conditions	Unit	Value
Main components				
base oil				mineral oil
base oil				ester
thickener				lithium soap
Application related technical data				
marking	DIN 51 502	DIN 51 825		KPE2K-50
viscosity at (40°C)	DIN 51 562-1	base oil	mm ² /s	15
viscosity at (100°C)	DIN 51 562-1	base oil	mm ² /s	4
drop point	DIN ISO 2176		°C	> 190
consistency	DIN 51 818	DIN ISO 2137	NLGI grade	2
worked penetration	DIN ISO 2137	60DH	0.1 mm	265-295
oil separation	DIN 51 817	168h/40°C	percent in weight	< 6
lower operating temperature	DIN 51 805	≤ 1,400 hPa	°C	-50
upper operating temperature	DIN 51 821-2	F50 (A/1500/6000), 100h	°C	120
colour				yellow
density (at 20°C)	DIN EN ISO 3838		g/cm ³	0.88
water resistance	DIN 51 807-1	3h/90°C	Degree	1-90
DN value (dm x n)			mm/min	1,000,000
four-ball test rig welding load	DIN 51 350-4		N	2,400
SKF-EMCOR	DIN 51 802	7 days, distilled water	corr. degree	0-1
SKF-EMCOR Copper	DIN 51 811	24h, 100°C	corr. degree	1
Product specific technical data				
biodegradability	CEC-L-33-A94	21 days	%	> 70

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47
 82216 Maisach
 +49 8142 3051 - 500
 info@oks-germany.com
 www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Product restricted to professional users. Safety data sheet available for download at www.oks-germany.com
 Our Customer and Technical service will be pleased to help should you have any further questions.